

MATT VINYL

A high opacity water-borne matt emulsion for interior use on wall and ceiling surfaces.

AVAILABILITY

Colour range See Crown Trade Literature.

Packaging 250mls, 1, 2.5, and 10 litre.

PROPERTIES

Drying time Under normal drying conditions touch dry 1-2 hours, recoatable after 4 hours. Allow for adequate ventilation during the drying period.

Finish Matt.

Composition Pigment: Titanium Dioxide, coloured pigments and extenders.
Binder: Vinyl acetate copolymer.
Solvent: Water.

Spreading rate 14m² per litre on smooth surfaces.

Wet film thickness 71 micrometres at 14m² per litre.

Dry film thickness 33 micrometres at 14m² per litre.

Volume solids 46% Brilliant White other colours will vary.

Flash point Not applicable.

VOC content EU limit value for this product (cat.A/a): 75 g/l (2007) / 30 g/l (2010)
This product contains max. 17 g/l VOC.

Limitations For interior use only. Do not apply when air or substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period.

PREPARATION

New surfaces All surfaces must be sound, clean, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied. Powdery, polished plaster or dense surfaces should be primed with Crown Trade Alkali Resting Primer. Porous surfaces should be 'mist' coated with Crown Trade Matt Vinyl thinned with up to 20% clean water.

Previously decorated surfaces

All surfaces must be sound, clean, suitably dry and free from anything that will interfere with the adhesion of the materials to be applied e.g. dirt, grease etc. Remove all loose, failing or suspect paint. Feather edges of sound paint. Remove all dust. Organic growth must be removed and the areas treated with Crown Trade Fungicidal Solution. Fill any fixing holes, cracks and shallow surface defects with Sandtex Trade Ready Mixed Filler. Patch prime bare and filled areas with Crown Trade Alkali Resting Primer thinned as per the container instructions. Wash remaining sound paint with hot water and liquid detergent solution to remove any contaminants, frequently changing the water. Any glossy or eggshell surfaces should be wet abraded to provide a key. Rinse with clean water to remove all residues. Allow to dry. If after cleaning any areas still contaminated with substances likely to cause staining and/or bleeding, patch prime with one coat of Crown Trade Alkali Resting Primer. Bring forward patch primed areas with one coat of Crown Trade Matt Vinyl.

COATING SYSTEM Apply two coats as required.

APPLICATION Stir well before use. Apply by brush or roller. For airless spray (dilution may be required). For further information contact the Akzo Nobel Customer Advice Centre.

CLEANING Return surplus material to container. Wash with clean water immediately after use.

HEALTH AND SAFETY Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. For further information contact the Akzo Nobel Customer Advice Centre. When preparing all surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Akzo Nobel products are freely available from the place of purchase or the address below. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not empty into drains, watercourses or access routes to septic tanks.

GENERAL INFORMATION

Apply all products in accordance with BS 6150: 2006 Code of practice for painting of buildings and BS 8000: Part 12: 1989 Code of practice for decorative wallcoverings and painting. Under normal and frost free conditions this product will remain usable for up to two years if stored correctly and unopened.

Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Akzo Nobel Decorative Coatings Ltd. is unable to guarantee results as it has no control over the conditions under which its products are applied.

For help or more information contact the Akzo Nobel Customer Advice Centre 0870 241 6457. Before using this product please ensure you have the latest information. The information is correct at date of issue Aug 2006.

